




VRLA Battery Technology for Military Vehicle Applications

Advanced Automotive Battery Conference 05 Presented to the

Mr. Fred Krestik

United States Army RDECOM 13 June 2005



maintaining the data needed, and c including suggestions for reducing	lection of information is estimated to ompleting and reviewing the collect this burden, to Washington Headqu uld be aware that notwithstanding ar DMB control number.	ion of information. Send comments arters Services, Directorate for Infor	regarding this burden estimate of mation Operations and Reports	or any other aspect of th , 1215 Jefferson Davis l	is collection of information, Highway, Suite 1204, Arlington	
1. REPORT DATE 13 JUN 2005		2. REPORT TYPE N/A		3. DATES COVERED -		
4. TITLE AND SUBTITLE				5a. CONTRACT NUMBER		
VRLA Battery Tec	chnology for Militar	y Vehicle Application	ons	5b. GRANT NUM	IBER	
				5c. PROGRAM E	LEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NU	MBER	
Fred Krestik			5e. TASK NUMBER			
				5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) USA TACOM 6501 E 11 Mile Road Warren, MI 48397-5000			8. PERFORMING ORGANIZATION REPORT NUMBER 14837			
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S) TACOM TARDEC		
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAIL Approved for publ	LABILITY STATEMENT ic release, distributi	on unlimited				
13. SUPPLEMENTARY NO U.S. government V Conference 05	otes V ork; not copyright o	ed in the U.S. Preser	nted at Advanced	Automotive	Battery	
14. ABSTRACT						
15. SUBJECT TERMS						
16. SECURITY CLASSIFIC	ATION OF:		17. LIMITATION OF	18. NUMBER	19a. NAME OF	
a. REPORT b. ABSTRACT c. THIS PAGE SAR unclassified unclassified unclassified		OF PAGES 12	RESPONSIBLE PERSON			

Report Documentation Page

Form Approved OMB No. 0704-0188



Agenda



Status Quo: 6TMF Battery

Changes in Vehicle Battery Usage Profiles

AGM Battery Evaluations

Pros & Cons of AGM Battery

VRLA Specification: MIL-PRF-32143


•QPL Efforts



Status Quo: 6TMF Battery



- Flooded Lead-Acid
- NATO Standard Size
- Fits >95% U.S. Military Vehicles
- 120 Ah (C/20)
- "Maintenance Free" Pb/Ca Grid Technology





Traditional Battery Usage Profile



Typical military trucks traditionally:

 Used vehicle batteries for powering Starting, Lighting, and Accessories Used vehicle batteries to power radios

was of little value for most tactical vehicle applications. A vehicle battery's deep discharge cycling capability



Today's Battery Usage Profiles



Many military vehicles today use vehicle batteries for powering:

Starting, Lighting, Accessories

Electronic equipment suites


Extended "engine-off" operation

Silent Watch

The vehicle battery's deep discharge cycling performance is critical for many modern vehicle applications.



AGM Battery Evaluations



- Initial Safety testing completed, March 2001
- Limited field testing Ft. Hood, August 2001
- Profiling to modified FLA spec completed Oct. 2001
- Larger Ft. Hood/Ft. Carson field test initiated **July 2002**
- Various laboratory cycling tests, April 2001 present



AGM Battery: Pros & Cons



Pros:


- Maintenance Free/ Longer Service Life
- Air Transportable
- Filled and Charged at factory
- Significantly longer shelf life (2+yrs vs. 6+ month)
- Deep Cycle performance: improved engine-off capabilities
- No stratification effects
- Direct replacement to the 6T series

Cons:

- Cost: Sole source item currently being procured by DLA as a commercial item (\$232 vs. \$68)
- Weight: 13-16 lbs heavier then the flooded 6TMF
- Reduced Performance/Life when mixed with 6TMF (Not recommended)



Procurement Strategy



batteries with the ultimate goal of developing a To promote competition and lower unit cost, a performance spec was developed for VRLA Qualified Products List. (QPL)

- Performance Specification developed, Feb 2004
- Solicitation to Industry, Feb 2004
- Qualification Testing began August 2004



Comparison of Key Battery Spec Requirements



Requirement	6TMF	VRLA
Nominal Weight	34 kg	40.5 kg max
Full Charge Capacity	120 ah	120 ah
Reserve Capacity(min)	200 minutes	230 minutes
Low Temperature Capacity (min)	() ()	
(discharge time to 7.2 volts) -18° C:	725 amp 30 sec	800 amp 30 sec
- 40° C:	350 amp 30 sec	400 amp 30 sec
Life Cycle Capacity (min)	235 cycles	360 cycles
Retention of Charge: (min)		
Reserve Capacity after 60 days:	175 minutes	
Reserve Capacity after 90 days:		200 minutes
Vibration Resistance (min)		
Reserve Capacity	190 minutes	219 minutes
Deep cycle capacity (min)	N/A	120 cycles
High Temperature Cycling (min)	N/A	200 cycles
Induced Destructive Overcharge (min)	N/A	Applies



QPL Status



- submitting battery samples for Qualification. Multiple vendors have expressed interest in
- Qualification testing is underway for two sets of battery samples.
- When two different vendors have successfully completed Qualification testing, the QPL will be established.



Conclusion



- VRLA batteries offer some desirable performance advantages for military vehicle applications.
- The Army is looking for alternative sources of supply for military-sized VRLA batteries.
- Copies of MIL-PRF-32143 are available to potential suppliers of VRLA batteries.



Thank-you!



For further information please contact:

Fred Krestik 586-574-8000 krestikf@tacom.army.mil U.S. Army RDECOM AMSRD-TAR-E/PWR/267 6501 East 11 Mile Road Warren, MI 48397-5000